

LISTING OF THE CLAIMS

1. **(Previously Presented)** Carrier comprised of a core and a polymer coating,
 wherein said coating contains a conductive polymer contained in a carbon black matrix,
 wherein said conductive polymer is formed by the in situ polymerization of said conductive polymer onto said carbon black matrix,
 wherein said conductive polymer is selected from the group consisting of polypyrrole and polyaniline;
 and wherein said conductive polymer is present in an amount of about 0.1 percent by weight of said polymer coating.
2. **(Original)** A carrier in accordance with **claim 1** wherein the polymer coating is comprised of a mixture of polymers.
3. **(Original)** A carrier in accordance with **claim 2** wherein the mixture is comprised of two polymers.
4. **(Original)** A carrier in accordance with **claim 2** wherein the mixture is comprised of two polymers not in close proximity in the triboelectric series.
5. **(Original)** A carrier in accordance with **claim 2** wherein the mixture is comprised of from about 2 polymers to about 7 polymers.
6. **(Original)** A carrier in accordance with **claim 1** wherein the conductive polymer is a polypyrrole coated on carbon black.

7. **(Original)** A carrier in accordance with **claim 6** wherein the polymer possesses a weight average molecular weight M_w of from about 10,000 to about 400,000, or possesses a weight average molecular weight of from about 20,000 to about 100,000.

8. **(Original)** A carrier in accordance with **claim 6** wherein said polymer possesses an M_w of from about 22,000 to about 75,000, and an M_w/M_n ratio of from about 1.4 to about 2.

9. **(Cancelled).**

10. **(Cancelled).**

11. **(Cancelled).**

12. **(Cancelled).**

13. **(Original)** A carrier in accordance with **claim 1** wherein said core diameter is from about 30 to about 100 microns.

14. **(Original)** A carrier in accordance with **claim 1** wherein said core is iron, steel or a ferrite.

15. **(Currently Amended)** A carrier in accordance with **claim 1** wherein said coating polymer ~~is~~ comprises a styrene polymer.

16. **(Currently Amended)** A carrier in accordance with **claim 1** wherein said polymer coating ~~is~~ comprises polyvinylidene fluoride, polyethylene, polymethyl methacrylate, polytrifluoroethylmethacrylate, copolyethylene vinylacetate, copolyvinylidene fluoride, polytetrafluoroethylene, polystyrene, polyvinyl chloride, polyvinyl acetate, or mixtures thereof.

17. **(Currently Amended)** A carrier in accordance with **claim 1** wherein said polymer coating is comprises polymethylmethacrylate, polystyrene, polytrifluoroethyl methacrylate, or mixtures thereof.

18. **(Original)** A carrier in accordance with **claim 1** wherein said polymer coating is comprised of a mixture of polymethylmethacrylate and polytrifluoroethyl methacrylate.

19. **(Original)** A carrier in accordance with **claim 1** wherein said polymer coating is present in an amount of from about 0.5 to about 10 percent by weight of said carrier, or from about 1 to about 5 percent by weight of said carrier.

20. **(Original)** A carrier in accordance with **claim 2** with a conductivity of from about 10^{-15} to about 10^{-4} (ohm-cm)⁻¹.

21. **(Original)** A carrier in accordance with **claim 2** with a triboelectric charge value of from about -60 to about 60 microcoulombs/gram and a conductivity of from about 10^{-12} to about 10^{-6} (ohm-cm)⁻¹.

22. **(Cancelled).**

23. **(Original)** A developer comprised of the carrier of **claim 1** and toner.

24. **(Original)** A developer in accordance with **claim 23** wherein said toner is comprised of a thermoplastic resin, colorant, and optionally toner additives, and optionally wherein said additives are charge additives, wax, surface additives and mixtures thereof.

25. **(Currently Amended)** A carrier in accordance with **claim 1** wherein said ~~coating contains therein or thereon a~~ the conductive polymer is of polyaniline and the polyaniline is segments attached to Lignin.

26. **(Cancelled).**

27. **(Currently Amended)** Carrier comprised of a core, a polymer coating, and wherein said coating contains a mixture of a polypyrrole and carbon black particles, and wherein said ~~polypyrrole~~ mixture is formed by the in situ polymerization of said ~~pyrrole~~ polypyrrole on the surface of said carbon black particles, and wherein said polypyrrole is present in an amount of about 0.1 percent by weight of said polymer coating.

28. **(Previously Presented)** Carrier comprised of a core, a polymer coating, and wherein said coating contains a mixture of a polyaniline and carbon black particles, and wherein said mixture is formed by the in situ polymerization of said polyaniline on the surface of said carbon black particles, and wherein said polyaniline is present in an amount of about 0.1 percent by weight of said polymer coating.

29. **(Original)** A carrier in accordance with **claim 1** wherein said coating contains a mixture of said polypyrrole and said polyaniline.

30. **(Currently Amended)** Carrier consisting essentially of a core and a polymer coating, and

wherein said coating contains a conductive polymer contained in a carbon black matrix;, and a polyaniline contained in a carbon black matrix, and wherein said ~~conductive polypyrrole polymer~~ is formed by the in situ polymerization of said ~~pyrrole~~ a polypyrrole onto said carbon black surface matrix, and wherein said polyaniline is formed by the in situ polymerization of said polyaniline onto said carbon black surface matrix, and wherein said polypyrrole is present in an amount of about 0.1 percent by

weight of said polymer coating, and wherein said polyaniline is present in an amount of about 0.1 percent by weight of said polymer coating.

31. **(Previously Presented)** Carrier comprised of a core and a polymer coating,

wherein said polymer coating contains a conductive polymer contained in a carbon black matrix;

wherein said conductive polymer is formed by the in situ polymerization of said conductive polymer onto said carbon black surface matrix;

wherein said conductive polymer has a weight average molecular weight Mw of from about 10,000 to about 400,000 or from about 20,000 to about 100,000;

wherein said conductive polymer is present in an amount of about 0.1 percent by weight of said polymer coating; and

wherein said conductive polymer is selected from the group consisting of polyaniline and polypyrrole.